

# TECHNICAL DATASHEET ALUMINIUM TAPE

## **Description & Uses**

Cromar AlphaChem Aluminium Tape is an 30 micron foil tape with an aggressive solvent acrylic adhesive protected by an easy release liner. It has an excellent peel adhesion as well as being water and fire resistant.

Tested to BS476 Part 6 & 7 Standards and meets Class 1 and Class 0 Fire Regulations.

#### Ideal for:

- Sealing joints / seams against moisture and vapour.
- Holding, splicing or masking applications requiring protection offered by foil backing.
- Duct sealing on ventilation and air conditioning

#### **Directions**

- Ensure all surfaces are clean, sound and dry.
- Remove the outer packaging from the tape.
- Peel the amount of tape required and apply.
- Finish by either tearing or cutting when finished.

# Storage

Store in cool, dry conditions between +5°C and +25°C.

### Limitations

- If using a knife to cut the tape, ensure to be careful of the blade use responsibly.
- It is the user's responsibility to ensure suitability for use.

## **Technical Data**





Adhesive	Solvent Acrylic
Backing Thickness	30 micron (Test Method: PSTC-133 / ASTM D 3652)
Total Thickness	55 micron (Test Method: PSTC-133 / ASTM D 3652)
Adhesion to Steel	15 N/25mm (Test Method: PSTC-101 / ASTM D 3330)
<b>Total Rolling Ball</b>	15cm (Test Method: PSTC-6 / ASTM D 3121)
Tensile Strength	45N/25mm (Test Method: PSTC-131 / ASTM D 3759)
Elongation	3.0% (Test Method: PSTC-131 / ASTM D 3759)
Service Temperature	-30°C ~ +120°C
<b>Application Temperature</b>	+10°C ~ +40°C

#### **Further Information:**

In the event of further queries or problems concerning the use of this product, please contact the address below, e-mail <a href="mailto:info@cromar.uk.com">info@cromar.uk.com</a>.

All products should be sold in accordance with the manufacturer's instructions. The manufacturer cannot be held responsible where conditions of use are beyond our control. Cromar Building Products Limited products' are available for sale in accordance with Cromar Building Products Limited standard conditions of sale, which is available upon request. Whilst any information contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendations, agents, or distributors, as the conditions of use and any labour involved are beyond our control. Our warranty is therefore limited to the quality of supplied product.